

# GC 3068HT

## PRODUCTIVITY GRINDING AIDS

Increase production capacity and quality of cement.

### PRODUCT PROPERTIES:

- Improve grinding efficiency.
- Reduce production costs.
- Increase cement quality (fineness, distribution of cement particles, etc.).
- Improve storage and transportation properties of cement.

### AREAS OF APPLICATION:

- Grinding cement according to EN 197-1 standard from type I to type V and high-aluminum cement.
- Grind all types of cement according to ASTM.
- Grind all types of cement according to TCVN.
- Suitable for ball mill, vertical mill and horromill.

### APPLICATION NOTES:

- **GC 3068HT** is an active grinding aid designed to increase the productivity of grinding stations and improve cement quality. Reduce mill costs at the same fineness of cement.
- Increase crusher productivity (from 8% to 20%), depending on the efficiency of the equipment and the characteristics of the grinding material.
- Improve the efficiency of closed-cycle mills by preventing adhesion on the grinding equipment, baffles and liners while still ensuring the smoothness of the cement.
- Due to the reduced re-agglomeration of particles after grinding, the amount of reflux to the crusher is reduced, thereby improving the efficiency of grinding aid.
- The volume of cement increases and the flexibility of cement increases during transportation.
- Can be pumped directly into the crusher or onto the conveyor belt that transports raw materials before the crusher.
- Absolutely do not mix with other products.
- Can be used with all standard cement types as well as sulfate resistant cement.
- Does not contain any hazardous substances. It is safe for use with standard precautions followed in the construction industry, such as use of hand gloves, safety goggles, etc.
- Avoid contact with foodstuffs and utensils. Avoid prolonged skin contact. In the event of contamination, wash thoroughly with water. If the eyes or mouth are affected, wash with clean water and obtain medical attention immediately.
- Store in a cool, dry place, away from direct sunlight.

#### MC-BIFI BAUCHEMIE JSC.

**Ha Noi:** 814/3 Lang Str., Lang Thuong Wd., Dong Da Dist., Hanoi City

**Da Nang:** 91 Le Van Duyet Str., Nai Hien Dong Wd., Son Tra Dist., Da Nang City

**HCMC:** No. Y13, Str. 29, Phuoc Kien A RLA, Phuoc Kien Commune, Nha Be Dist., HCMC

**Email:** info@mcbifi-bauchemie.vn | **Website:** www.mcbifi-bauchemie.com

- Tel: (+84) 24 3775 5312 - Fax: (+84) 24 3775 9607

- Tel: (+84) 23 6355 6869 - Fax: (+84) 23 6355 6969

- Tel: (+84) 28 3620 8665 - Fax: (+84) 28 3620 8685

**TECHNICAL DATA:**

Characteristic	Unit	Value	Comments
Density	kg/dm <sup>3</sup>	1.070 ± 0.05	
Dosage	kg	0.6 – 1.2	Per 1000 kg of cement
pH-Value (20°C)	°C	9 ± 2	
Alkaline content	%	< 1.0	NaOH equivalent

**PRODUCT CHARACTERISTICS:**

Standard	Complies with ASTM C465-16
Color	Brown-Black
Physical state	Liquid
Shelf-life	12 months
Packaging	200 L drums
	1000 L IBC tanks
	Tank trucks

Note: The information on this data sheet is based on our experiences and correct to the best of our knowledge. It is, however, not binding. It has to be adjusted to the individual structure, application purpose and especially to local conditions. Our data refers to the accepted engineering rules, which have to be observed during application. This provided we are liable for the correctness of this data within the scope of our terms and conditions of sale-delivery-and-service. Recommendations of our employees which differ from the data contained in our information sheets are only binding if given in written form. The accepted engineering rules must be observed at all times.

Edition **11/23**. Some technical changes have been made to this print medium. Older editions are invalid and may not be used anymore. If a technically revised new edition is issued, this edition becomes invalid.