

MC-Centrament WP 100

Waterproofing admixture for concrete.

PRODUCT PROPERTIES:

- Increase waterproofing resistance.
- Plasticize ready-mix concrete and mortar.
- Enhance corrosion resistance, protect concrete and steel against seawater intrusion.
- Resist frequent expansion and contraction.
- Free of corrosive components.

AREAS OF APPLICATION:

- Walls and floor, sink, pile, line of sight, silo and reservoir.
- Panel, mortar plaster less cement, walls and the tank floor.
- Concrete structure need to surface plaster.
- Block concrete and brick.

APPLICATION NOTES:

- **MC-Centrament WP 100** is a new generation of concrete admixture based on modified polymer Polycarboxylate technology with superior high range water reducing to enhance the early and ultimate strength.
- It can be added directly to the gauging water prior to its addition to the dry mixed aggregates or simultaneously with the gauging water at the batching plant.
- Trial mixes are recommended to establish exact dosage rates required to suit individual requirements. Significant overdosage will result in increased setting time of the concrete. However, provided concrete is cured effectively, ultimate strength and properties will not be affected.
- We can supply accurate dispensing equipment upon request.
- Use an appropriate mixer and do not mix by hand. If assistance is required, please contact our Technical Service Department.
- **MC-Centrament WP 100** is compatible to all standard cement types as well as sulfate resistant cement.
- Does not contain any hazardous substances. It is safe for use with standard precautions followed in the construction industry, such as use of hand gloves, safety goggles, etc.
- Avoid contact with foodstuffs and utensils. Avoid prolonged skin contact. In the event of contamination, wash thoroughly with water. If the eyes or mouth are affected, wash with clean water and obtain medical attention immediately.

MC-BIFI BAUCHEMIE JSC.

Ha Noi: 814/3 Lang Str., Lang Thuong Wd., Dong Da Dist., Hanoi City

Da Nang: 91 Le Van Duyet Str., Nai Hien Dong Wd., Son Tra Dist., Da Nang City

HCMC: No. Y13, Str. 29, Phuoc Kien A RLA, Phuoc Kien Commune, Nha Be Dist., HCMC

Email: info@mcbifi-bauchemie.vn | **Website:** www.mcbifi-bauchemie.com

- Tel: (+84) 24 3775 5312 - Fax: (+84) 24 3775 9607

- Tel: (+84) 23 6355 6869 - Fax: (+84) 23 6355 6969

- Tel: (+84) 28 3620 8665 - Fax: (+84) 28 3620 8685

**TECHNICAL
DATA:**

Characteristic	Unit	Value	Comments
Density	g/cm ³	1.1 ± 0.05	
Recommended dosage	Litre	0.2 – 0.5	per 100 kg of binder
Max. Chloride content	%	per weight < 0.1	

**PRODUCT
CHARACTERISTICS:**

Standard	Complies with ASTM C494 & TCVN 8826 Type A
Consistency	Liquid
Expiry	8 months
Form of delivery	200 L drums 1000 L IBC tanks Tank trucks

Property specifications are based on laboratory tests and may vary in practical application. To determine the individual technical suitability, preliminary suitability tests should be carried out under the application conditions.

Color: Admixture's color can be changed due to the reaction between polymer component within admixture's composition with UV from sunlight. This phenomenon does not affect to admixture's quality in its shelf-life. We recommend users to store product into covered area to protect from direct sunlight in order to avoid mentioned changing.

Note: The information on this data sheet is based on our experiences and correct to the best of our knowledge. It is, however, not binding. It has to be adjusted to the individual structure, application purpose and especially to local conditions. Our data refers to the accepted engineering rules, which have to be observed during application. This provided we are liable for the correctness of this data within the scope of our terms and conditions of sale-delivery-and-service. Recommendations of our employees which differ from the data contained in our information sheets are only binding if given in written form. The accepted engineering rules must be observed at all times.

Edition **11/23**. Some technical changes have been made to this print medium. Older editions are invalid and may not be used anymore. If a technically revised new edition is issued, this edition becomes invalid.