

# MC-Injekt GL-95

Swelling, flexible, waterproofing acrylate gel sealant for injection in concrete, masonry and foundation soil.

## PRODUCT PROPERTIES:

- Very low-viscosity acrylic-based hydrogel.
- Very good injectability.
- Readily controllable injection path propagation thanks to controllable reaction time.
- Very low application temperature.
- Reliable sealing/waterproofing due to high elasticity and good swelling capacity.
- Durably water-impermeable in moist media.
- General building authority approval issued by DIBt for injection into soil and groundwater.
- Fulfills the UBA (German environmental agency) guidelines for sealants in contact with potable water.
- High chemical resistance especially in highly alkaline environments.
- REACH exposure: water contact permanent, inhalation periodic, processing and application.
- Environmental Product Declaration EPD.

## AREAS OF APPLICATION:

- Swelling flexible filling sealant for cracks and cavities in permanently damp concrete and masonry.
- Subsequent vertical sealing of masonry.
- Subsequent formation of a horizontal barrier/DPC in masonry.
- Injection of waterproofing membrane into interstitial spaces between buildings.
- Injection of waterproofing membrane into foundation soil (curtain injection).

## APPLICATION NOTES:

- **Preparatory measures:** Prior to injection, an investigation of the structure and of any leaks must be carried out according to the state of the art and the rules of technology, and an injection concept must be planned. Packers must be set before injection. A trial injection is recommended.
- **Mixing the components:**
  - Components A and B of **MC-Injekt GL-95** are prepared from their respective subcomponents in the specified mixing ratio. Component A is mixed from subcomponents A1, A2 and A3. To do this, pour component A2 and A3 into the container of component A1 and stir energetically with a wooden paddle. Component B is dissolved in water and mixed with a wooden paddle. The reaction times of **MC-Injekt GL-95** depend on the volume of component B added to water.
  - Mixing of the components A and B thus prepared takes place during injection: The components are mixed as they pass through the mixing head of the MC-I 710 injection pump (mixing distance > 10 cm inline static mixer).

### MC-BIFI BAUCHEMIE JSC.

**Ha Noi:** 814/3 Lang Str., Lang Thuong Wd., Dong Da Dist., Hanoi City

**Da Nang:** 91 Le Van Duyet Str., Nai Hien Dong Wd., Son Tra Dist., Da Nang City

**HCMC:** No. Y13, Str. 29, Phuoc Kien A RLA, Phuoc Kien Commune, Nha Be Dist., HCMC

**Email:** info@mcbifi-bauchemie.vn | **Website:** www.mcbifi-bauchemie.com

- Tel: (+84) 24 3775 5312 - Fax: (+84) 24 3775 9607

- Tel: (+84) 23 6355 6869 - Fax: (+84) 23 6355 6969

- Tel: (+84) 28 3620 8665 - Fax: (+84) 28 3620 8685

○ **Reaction time with addition of component B in 25L or 100L of water:**

| %            | 25L water | 100L water | Reaction time |
|--------------|-----------|------------|---------------|
| approx. 0,2% | 0,05kg    | 0,2kg      | approx. 90s   |
| approx. 0,5% | 0,125kg   | 0,5kg      | approx. 47s   |
| approx. 1%   | 0,25kg    | 1,0kg      | approx. 30s   |
| approx. 2%   | 0,5kg     | 2,0kg      | approx. 21s   |
| approx. 4%   | 1,0kg     | 4,0kg      | approx. 16s   |

- **Delayed reaction:** The reaction time of **MC-Injekt GL-95** can be extended with MC-Injekt Retarder GL. The retarder is added to the ready-mixed component A. The amount added determines the de- layed reaction time. This mixture can be used within 2 hours. When using retarder, the concentration of component B of 0.5% must be adhered to.

**Reaction time when adding MC-Injekt Retarder GL in 30.1 kg or 120 kg component A**

| %    | 30,1 kg | 120 kg | Reaction time |
|------|---------|--------|---------------|
| 2,5% | 0,75kg  | 3kg    | ca. 9 mins    |
| 3%   | 0,90kg  | 4kg    | ca. 17 mins   |
| 5%   | 1,50kg  | 6kg    | ca. 50 mins   |

- **Equipment cleaning:** Within the working time of the resin, all tools can be cleaned with water or air. Material that has reacted or set will need to be removed mechanically.
- **Injection:**
  - Injection is performed with the two components being mixed as they are dispensed by the MC-I 710 injection pump.
  - MC-Hammer Packer LP 18 or MC-Hammer Packer LP 12 packers are recommended for injection into building components. MC-Bore Packer LS 18 packers or injection lances are recommended for injection into foundation soil.
  - Application work should cease once component/subsoil temperatures fall below 1°C.
  - Ensure compliance with the information given in the specifications and the Safety Data Sheets.

#### TECHNICAL DATA:

| Characteristic         | Unit               | Value   | Comments   |
|------------------------|--------------------|---|--|
| Mixing ratio           | Parts by volume    | 1 : 1   | Comp. A : Com. B in solution   |
| Canister               | Mass fractions     | 27.6 : 0.5 : 2  | Comp. A1 : Comp. A2 : comp. A3   |
| Drum                   |                    | 110 : 2 : 8   | Comp. A1 : Comp. A2 : comp. A3   |
| Canister (variable)    |                    | 30.1 : 25.125   | Comp. A : Comp. B in solution  |
| Drum (variable)        |                    | 120 : 100.5<br>0.5 : 100  | Comp. A : Comp. B in solution<br>Comp. B : Water (standard)                                    |
| Density                | Kg/dm <sup>3</sup> | Approx. 1.1<br>Approx. 1.2<br>Approx. 0.97<br>Approx. 1.06<br>Approx. 1.2 - 1.5 | DIN 53479<br>Mixture<br>Component A1<br>Component A2<br>Component A3<br>Comp. B (bulk density) |
| Viscosity              | mPa·s              | Approx. 5   | EN ISO 3219  |
| Working time           | seconds            | Approx. 16 - 90   |  |
| Application conditions | °C                 | 1 - 40  | Component and subsoil temperature  |
| PH value               |                    | Approx. 9.5   | cured product  |

*\*All technical values are laboratory results determined at 21°C ±2°C and 50% relative humidity.*

#### PRODUCT CHARACTERISTICS:

|                           |  |
|---------------------------|--|
| <b>Color</b>              | Blue   |
| <b>Cleaning agent</b>     | Water  |
| <b>Delivery form</b>      | MC-Injekt GL-95, component A1, 27.6 kg and 110 kg containers<br>MC-Injekt GL-95, component A2, box of 4 x 0.5 kg containers<br>MC-Injekt GL-95, component A3, 2 kg and 8 kg containers<br>MC-Injekt GL-B, component B, box of 4 x 0.5 kg containers<br>MC-Injekt Retarder GL, 5 kg container |
| <b>Storage</b>            | Can be stored in original sealed packages at temperatures between 5°C and 25°C in dry conditions for at least 12 months.   |
| <b>Packaging disposal</b> | Make sure single-use containers are completely empty. Ensure compliance with our information leaflet "Return of Emptied Transportation and Sale Packaging".<br>We will be glad to send you this on request.  |

**Note:** The information provided here is based on our experience and correct to the best of our knowledge. It is, however, not binding. It will need to be adapted to the requirements of the individual building projects, to the specific application and to non-standard local conditions. Our data refers to the accepted engineering rules, which have to be observed during application. Given these preconditions we shall be liable for the accuracy of the information given as outlined in our sales and delivery terms and conditions. Recommendations by our employees that deviate from this information are only binding for us if they have been confirmed in writing. In all cases, the generally accepted rules and practices reflecting the current state of the art must be adhered.

Edition **01/2024**. Some technical changes have been made to this print medium. Older editions are invalid and may not be used.