

MC-TechniFlow 1103

Superplasticizer concrete admixture.

PRODUCT PROPERTIES:

- High water reduction ability.
- Improve good slump retention.
- Increase high early and ultimate strength of concrete.
- Reduce shrinkage and creep, suitable for runway concrete.
- Free of corrosive components.

AREAS OF APPLICATION:

- Cast-in-place concrete.
- Massive concrete.
- Average time transport distances.
- Prolonged concrete pouring time.
- High temperature environment.

APPLICATION NOTES:

- **MC-TechniFlow 1103** plasticize concrete mix, improve workability.
- Increased setting time and slump retention, easier placing.
- Increased compressive strength and flexural strength, increased waterproofing and shrinkage.
- It can be mixed directly into measured water before adding to dry concrete mix or added to wet mixed concrete, should be mixed for at least 1 minute.
- Trial mixes are recommended to establish exact dosage rates required to suit individual requirements. When accidental overdosing occurs, the set retarding effect increases. However, the final strength will not be affected if this period has right curing.
- We can provide accurate dispensing equipment upon request.
- Use an appropriate mixer and do not mix by hand. If assistance is required, please contact our Technical Service Department.
- Can be combined with all MC-BIFI products but must be mixed separately.
- Can be used with all standard cement types as well as sulfate resistant cement.
- Does not contain any hazardous substances. It is safe to use with standard precautions followed in the construction industry, such as use of hand gloves, safety goggles, etc.
- Avoid contact with foodstuffs and utensils. Avoid prolonged skin contact. In case of contamination, it should be thoroughly rinsed with water. When splashed into eyes or mouth, wash thoroughly with clean water and obtain medical attention immediately.

MC-BIFI BAUCHEMIE JSC.

Ha Noi: 814/3 Lang Str., Lang Thuong Wd., Dong Da Dist., Hanoi City

Da Nang: 91 Le Van Duyet Str., Nai Hien Dong Wd., Son Tra Dist., Da Nang City

HCMC: No. Y13, Str. 29, Phuoc Kien A RLA, Phuoc Kien Commune, Nha Be Dist., HCMC

Email: info@mcbifi-bauchemie.vn | **Website:** www.mcbifi-bauchemie.com

- Tel: (+84) 24 3775 5312 - Fax: (+84) 24 3775 9607

- Tel: (+84) 23 6355 6869 - Fax: (+84) 23 6355 6969

- Tel: (+84) 28 3620 8665 - Fax: (+84) 28 3620 8685

**TECHNICAL
DATA:**

Characteristic	Unit	Value	Comments
Density	g/cm ³	1.04 ± 0.05	
Recommended dosage	Litre	0.6 – 1.6	per 100 kg of binder
Typical dosage	Litre	0.6 – 1.2	per 100 kg of binder
Max. Chloride content	%	per weight < 0.1	

**PRODUCT
CHARACTERISTICS:**

Standard	Complies with ASTM C494 & TCVN 8826 Type D
Consistency	Liquid
Expiry	8 months
Form of delivery	200 L drums 1000 L IBC tanks Tank trucks

Property specifications are based on laboratory tests and may vary in practical application. To determine the individual technical suitability, preliminary suitability tests should be carried out under the application conditions.

Color: Admixture's color can be changed due to the reaction between polymer component within admixture's composition with UV from sunlight. This phenomenon does not affect to admixture's quality in its shelf-life. We recommend users to store product into covered area to protect from direct sunlight in order to avoid mentioned changing.

Note: The information on this data sheet is based on our experiences and correct to the best of our knowledge. It is, however, not binding. It has to be adjusted to the individual structure, application purpose and especially to local conditions. Our data refers to the accepted engineering rules, which have to be observed during application. This provided we are liable for the correctness of this data within the scope of our terms and conditions of sale-delivery-and-service. Recommendations of our employees which differ from the data contained in our information sheets are only binding if given in written form. The accepted engineering rules must be observed at all times.

Edition **11/23**. Some technical changes have been made to this print medium. Older editions are invalid and may not be used anymore. If a technically revised new edition is issued, this edition becomes invalid.